

Atlantis Gold

Colores
Colours































Atlantis

V1 Variación gráfica uniforme
Uniform graphical variation

P Porcelánico
Porcelain  Pavimento
Floor tiles  Revestimiento
Wall tiles  Resistencia la helada
Frost resistance

| Medida nominal (cm) Nominal size | Espesor - E (mm) Thickness E | Tipología Typology | Deslizamiento Coefficient of friction |
|-------------------------------------|---------------------------------|-----------------------|--|
| 120 x 120 Polished Rect. | 10,7 | Bla - GL | - |
| 120 x 120 Satin Rect. | 9,0 | Bla - GL | - |
| 60 x 120 Polished Rect. | 10,5 | Bla - GL | - |
| 59,5 x 119,2 Satin Rect. | 9,0 | Bla - GL | - |
| 29,5 x 59,5 Matt Rect. | 8,0 | Bla - GL | CLASE 1 |
| 23,2 x 26,7 Hexa Matt Rect. | 9,0 | Bla - GL | - |
| 33 x 120 Peldaño Recto Matt | 12,0 | Ala - GL | CLASE 1 |

CARACTERÍSTICAS TÉCNICAS TECHNICAL FEATURES

| | ISO 13006 UNE-EN 14411 | Bla     | B1b   | B1a   | B111  |
|---|--|--|---|---|--|
|  Longitud y anchura Length and width | EN ISO 10545-2 | ± 0,6 % ± 2,0 mm | ± 0,6 % ± 2,0 mm | ± 0,6 % ± 2,0 mm | ± 0,5 % ± 2,0 mm |
|  Espesor Thickness | EN ISO 10545-2 | ± 5 % ± 0,5 mm | ± 5 % ± 0,5 mm | ± 5 % ± 0,5 mm | ± 10 % ± 0,5 mm |
|  Rectitud de lados Straightness of sides | EN ISO 10545-2 | ± 0,5 % ± 1,5 mm | ± 0,5 % ± 1,5 mm | ± 0,5 % ± 1,5 mm | ± 0,5 % |
|  Ortogonalidad Rectangularity | EN ISO 10545-2 | ± 0,5 % ± 2,0 mm | ± 0,5 % ± 2,0 mm | ± 0,5 % ± 2,0 mm | ± 0,3 % ± 1,5 mm |
|  Planitud de superficie Surface flatness | EN ISO 10545-2 | ± 0,5 % ± 2,0 mm | ± 0,5 % ± 2,0 mm | ± 0,5 % ± 2,0 mm | + 0,5 % ; - 0,3 % + 2 mm ; - 1,5 mm |
|  Absorción de agua Water absorption | EN ISO 10545-3 | E ≤ 0,5 % Max. Individual 0,6% | 0,5 % ≤ E ≤ 3 % | 3 % < E < 6 % Max. Individual 0,6% | E > 10 % |
|  Fuerza de rotura (N)* Breaking strength * | EN ISO 10545-4 | E > 7,5 mm > 1300 N E < 7,5 mm > 700 N | E > 7,5 mm > 1100 N E < 7,5 mm > 700 N | E > 7,5 mm > 1000 N E < 7,5 mm > 600 N | E > 7,5 mm > 600 N E < 7,5 mm > 200 N |
|  Resistencia a la flexión (N/mm²) Modulus of rupture | EN ISO 10545-4 | > 35 N/mm² Min. Individual 35 N/mm² | > 35 N/mm² Min. Individual 27 N/mm² | > 22 N/mm² Min. Individual 20 N/mm² | E > 7,5 > 12 N/mm² E < 7,5 > 15 N/mm² |
|  Resistencia a la abrasión profunda (Solo UGL) Surface deep abrasion resistance (Solo UGL) | EN ISO 10545-6 | Máx. 175 mm³ | Máx. 175 mm³ | Máx. 345 mm³ | No aplica Not apply |
|  Resistencia a la abrasión superficial (Solo GL) Surface abrasion resistance (Solo GL) | EN ISO 10545-7 | Valor declarado Declared value | Valor declarado Declared value | Valor declarado Declared value | No aplica Not apply |
|  Coeficiente de dilatación térmica lineal (1/k) Coefficient of linear thermal expansion | EN ISO 10545-8 | Valor declarado Declared value | Valor declarado Declared value | Valor declarado Declared value | Valor declarado Declared value |
|  Resistencia al choque térmico Thermal shock resistance | EN ISO 10545-9 | Resiste Resist | Resiste Resist | Resiste Resist | Resiste Resist |
|  Resistencia al cuarteo Crazing resistance | EN ISO 10545-11 | Resiste Resist | Resiste Resist | Resiste Resist | Resiste Resist |
|  Resistencia a la helada Frost resistance | EN ISO 10545-12 | Resiste Resist | No resiste Not resist | No resiste Not resist | No resiste Not resist |
|  Deslizamiento Coefficient of friction | UNE ENV 41901 DIN 51130 DIN 51097 ANSI A137.1 | Valor declarado Declared value | Valor declarado Declared value | Valor declarado Declared value | No aplica Not apply |
|  Resistencia a productos de limpieza y aditivos para piscina Resistance to household chemicals and swimming pool salts | EN ISO 10545-4 | Min GB | Min GB | Min GB | Min GB |
|  Resistencia a bajas concentraciones Resistance to low concentrations | EN ISO 10545-13 | GLA - ULA / GLB (Pulido) GLA - ULA / GLB (Polished) | GLA | GLA | GLA |
|  Resistencia a altas concentraciones Resistance to high concentrations | EN ISO 10545-13 | GHA - UHA / GHB (Pulido) GHA - UHA / GHB (Polished) | GHA | GHA | GHA |
|  Resistencia a las manchas Resistance to stains | EN ISO 10545-14 | > 3 | > 3 | > 3 | > 3 |

Las características indicadas son generales por grupo de absorción, para características concretas de modelo y color solicitar la ficha técnica correspondiente. The characteristics indicated are general for each absorption group, for specific characteristics of the model and color, please request the corresponding technical data sheet.

* E corresponde al espesor indicado en la tabla de la esquina superior derecha. E is the thickness shown in the upper right-hand corner of table.